



KANATOL-3430E

KANATOL-3430 E Primary Plasticizer for PVC and PVC copolymers

Chemical Nature Citric acid esters of mixed alcohols

Chemical Name	:-	N. A.
Trade Name	:-	KANATOL-3430 E
Molecular Formula	:-	Proprietary
Molecular Weight	:-	N. A.
Molecular Structure	:-	N. A.

Specification	Characteristics	Unit	Test Method	Value
	Colour	HU	ASTM-D-1045-2008	30 max.
	Volatile Loss (130°C/3Hrs)	wt. %	KLJTM	0.60 max.
	Ester Value	mg KOH/g	ASTM-D-1045-2008	388 ± 3.
	Acid Value	mg KOH/g	ASTM-D-1045-2008	0.6 max.
	Moisture	wt. %	ASTM-E-203-2005	0.6 max.
	Specific Gravity (27°C)		ASTM-D-1045-2008	0.995 ± 0.001
	Ester content	wt. %	ASTM-D-1045-2008	99.5 min.
	Heat Stability (180°C/2Hrs)	HU	ISI-9591-2003	90 max.
	Plasticizing Esters by GC	% by area	KLJTM	99.50 min.
	Residual alcohol	% by area	KLJTM	0.10 max.

Typical Properties

Viscosity at 20°C	cp	KLJTM	21 ± 3
Refractive Index (27°C)	-	KLJTM	1.449 ± 0.002

Properties

KANATOL-3430 E is almost colourless and odourless oily liquid, free of foreign materials which is in soluble in water but soluble in alcohols, hexane etc. It is miscible and compatible with all the monomeric plasticizers of PVC compounding.



KANATOL-3430E



Application

1. Good substitute of costly ATBC for food packing products.
2. Plasticizer for precise instrument packaging.
3. REACH complaint, Phthalates free economic and eco-friendly ester for Inks, Paints, Vinyl floorings and Latex adhesives.
4. Safe Plasticizer for manufacturing Baby toys, nappies & Safety glasses.

Plasticizing Efficiency 0.93

Packing & Storage

KANATOL-3430 E is packed in 200/225 kg iron drum / HDPE drum, 20 - 22 fcl in Flexi tank or in road tanker. It is stored in tightly closed container, in a cool, dry & ventilated area.

Shelf Life

It keeps the original characteristics minimum for 24 month, if kept in recommended storage.

Safety

The MSDS can be provided on request.

Disclaimer

The data contained in this publication are based on our current knowledge and experience. During processing, there are so many factors which may affect the application part of **KANATOL-3430 E**, so these data neither imply any guarantee of certain properties, nor the suitability of the product for the specific purpose. Any data given in this publication may change without prior information and do not constitute the agreed quality of our product.

Total Solution in Plasticizers